

TECHNICAL SPECIFICATION

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
685	1.00	1.46
730	1.10	1.51
760	1.15	1.51
800	1.20	1.50
815	1.25	1.53
835	1.30	1.56
890	1.40	1.57
975	1.50	1.54

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
1025	1.60	1.56
1090	1.70	1.56
1115	1.75	1.57
1145	1.80	1.57
1230	1.90	1.54
1290	2.00	1.55
1385	2.20	1.59
1495	2.40	1.61

BRIGHTNESS

TOP / BACK	85%	ISO 2470 (Photovolt)
MOISTURE	7%	ISO 287

TOLERANCES

SUBSTANCE	+/- 5%	average of order
MOISTURE	+ 2 / - 1	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
STIFFNESS	/	for single determinations (95% of values)
BRIGHTNESS	Lim. inf. - 2	for single determinations (95% of values)
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2
SAMPLING		ISO 186

CERTIFICATIONS: ISO 9001 / ISO 14001 / ISO 50001 / OHSAS 18001
FSC® C081817 - PEFC™ INT-PEFC/COC-001142 CERTIFIED BOARD IS AVAILABLE ON
REQUEST