



**VINCICOAT PLUS**  
**COATED WHITE LINED CHIPBOARD**  
**(WLC) WITH GREY BACK**  
**GD 1**

**TECHNICAL SPECIFICATION**

**FEBRUARY 2026**

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)			STIFFNESS L&W *(5°)		
			MD	CD		MD	CD	
ISO 536	ISO 534	ISO 534	ISO 2493		ISO 2493	DIN 53121		DIN 53121
<b>g/m<sup>2</sup></b>	<b>µm</b>	<b>cm<sup>3</sup>/g</b>	<b>mNm</b>	<b>mNm</b>	<b>√(md*cd)</b>	<b>mNm</b>	<b>mNm</b>	<b>√(md*cd)</b>
350	510	1.46	23.0	10.0	15.2	43.7	19.0	28.8
375	550	1.47	27.0	12.0	18.0	51.3	22.8	34.2
400	600	1.50	33.8	15.5	22.9	64.2	29.4	43.4
425	620	1.46	38.0	17.8	26.0	72.2	33.8	49.4
450	680	1.51	42.0	20.9	29.6	78.5	39.7	55.8

(\*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

**BRIGHTNESS**

TOP	82%	ISO 2470-2
-----	-----	------------

**COBB - ISO 535**

COBB BACK 60' (*)	<60 g/m <sup>2</sup>	ISO 535
COBB BACK 180' (*)	<60 g/m <sup>2</sup>	ISO 535

(\*) NON STANDARD TREATMENT, AVAILABLE ON REQUEST ONLY.

**TOLERANCES - SAMPLING ISO 186**

SUBSTANCE	+/- 2%	ISO 536
CALIPER	+/- 5%	ISO 534
STIFFNESS	- 15%	DIN 53 121
BRIGHTNESS	+/- 2	ISO 2470-2
TEST CONDITIONS	<b>T:</b> 23° C +/- 1	<b>RH:</b> 50% +/- 2

