



VINCICOAT PLUS

COATED WHITE LINED CHIPBOARD
(WLC) WITH GREY BACK
GD 1

Provisional TECHNICAL SPECIFICATION

JANUARY 2025

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)			STIFFNESS L&W *(5°)		
			MD	CD		MD	CD	
ISO 536	ISO 534	ISO 534	ISO 2493		ISO 2493	DIN 53121		DIN 53121
g/m²	μm	cm³/g	mNm	mNm	√(md*cd)	mNm	mNm	√(md*cd)
350	510	1.46	23.0	10.0	15.2	43.7	19.0	28.8
375	550	1.47	27.0	12.0	18.0	51.3	22.8	34.2
400	600	1.50	33.8	15.5	22.9	64.2	29.4	43.4
425	620	1.46	38.0	17.8	26.0	72.2	33.8	49.4
450	680	1.51	42.0	20.9	29.6	78.5	39.7	55.8

(*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	82%	ISO 2470-2

COBB - ISO 535		
COBB BACK 60' (*)	<60 g/m ²	ISO 535
COBB BACK 180' (*)	<60 g/m ²	ISO 535

(*) NON STANDARD TREATMENT, AVAILABLE ON REQUEST ONLY.

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 2%	ISO 536
CALIPER	+/- 5%	ISO 534
STIFFNESS	- 15%	DIN 53 121
BRIGHTNESS	+/- 2	ISO 2470-2
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2