



TECHNICAL SPECIFICATION

SEPTEMBER 2020

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
800	1.20	1.50
882	1.40	1.59
945	1.50	1.59
1008	1.60	1.59
1071	1.70	1.59
1100	1.75	1.59
1134	1.80	1.59
1197	1.90	1.59
1260	2.00	1.59
1323	2.10	1.59
1386	2.20	1.59
1449	2.30	1.59
1512	2.40	1.59

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
1575	2.50	1.59
1701	2.70	1.59
1764	2.80	1.59
1827	2.90	1.59
1890	3.00	1.59
1953	3.10	1.59
2016	3.20	1.59
2079	3.30	1.59
2142	3.40	1.59
2205	3.50	1.59
2331	3.70	1.59
2394	3.80	1.59
2520	4.00	1.59

BRIGHTNESS		
TOP	/	ISO 2470
BACK	/	ISO 2470

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 5%	average of order
MOISTURE ISO 287	7.5% + 1.5 / - 1.0	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
BRIGHTNESS	/	for single determinations (95% of values)
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

CERTIFICATIONS: ISO 9001 / ISO 14001 / ISO 50001 / OHSAS 18001 / BLAUER ENGEL
 FSC® - C081817 - PEFC™ INT-PEFC/COC-001142 CERTIFIED BOARD IS AVAILABLE ON REQUEST

To download the certificate, please click

