



SERVIBOARD WR

Fully coated white lined chipboard, grey back / GD2 Water Repellent

Born to be converted

TECHNICAL SPECIFICATION

Substance	Caliper	Bulk	L&W 5°		Taber 15° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	DIN 53 121		ISO 2493	
g/m ²	mm	cm ³ /g	mNm	mNm	mNm	mNm
280	0.380	1.36	19.0	9.5	10.0	5.0
300	0.410	1.36	23.4	11.7	12.4	6.2
320	0.435	1.36	28.2	14.1	14.7	7.4
350	0.485	1.38	36.6	18.3	18.7	9.3

(*) L&W Werte sind garantiert; Taber Werte sind errechnet / L&W figures are guaranteed; Taber figures are calculated.

ISO 2470-2 Brightness (at production)

Top 84 % +/-1

Tolerances – Sampling ISO 186

Substance +/- 2 %

Caliper +/- 5 %

Bending Stiffness - 15 %

Cobb 60 back 20 - 60 g/m² ISO 535

Gloss 60° top >14 % Dr. Lange

Test conditions T: 23 +/- 1° C RH: 50 +/- 2%

Tolerances as agreed by the actual valid FFI (the association of the German carton makers)

Certified according to: ISO 9001
ISO 14001
EMAS
FSC®

FSC® - Certified Board is available on request

06-2017