



**TRIPLEX MADERA**  
**FULLY COATED WHITE LINED CHIPBOARD**  
**(WLC) WITH MANILA BACK**  
**GT 2**

**TECHNICAL SPECIFICATION**

**SEPTEMBER 2020**

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)		STIFFNESS L&W *(5°)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
<b>g/m<sup>2</sup></b>	<b>µm</b>	<b>cm<sup>3</sup>/g</b>	<b>mNm</b>	<b>mNm</b>	<b>mNm</b>	<b>mNm</b>
250	338	1.35	9.1	4.2	18.5	8.5
275	375	1.36	11.6	5.2	24.0	11.0
300	407	1.36	14.3	6.4	28.0	12.8
325	445	1.37	18.1	8.1	36.0	16.5
350	485	1.38	22.1	9.9	44.0	20.2
375	530	1.41	26.6	11.9	54.0	24.4
400	555	1.39	32.0	14.3	65.0	29.4
425	585	1.38	38.0	16.8	72.2	34.8
450	620	1.37	43.4	19.0	85.9	39.0

(\*) THE TABER VALUES ARE GUARANTEED; L&W FIGURES ARE CALCULATED.

<b>BRIGHTNESS</b>		
TOP	79.5%	ISO 2470-2

<b>TOLERANCES - SAMPLING ISO 186 (*)</b>	
SUBSTANCE	+/- 4%
CALIPER	+/- 5%
STIFFNESS	- 15%
BRIGHTNESS	+/- 1.5
TEST CONDITIONS	T: 23° C +/- 1

(\*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.

**CERTIFICATIONS:** ISO 9001 / ISO 14001 / ISO 50001 / ISO 45001  
 FSC® - C081817 - PEFC™ INT-PEFC/COC-001142 CERTIFIED BOARD IS AVAILABLE ON REQUEST

To download the certificate, please click

