

TECHNICAL SPECIFICATION

DECEMBER 2025

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mNm	mNm	mNm	mNm
(250)	328	1.31	7.0	2.8	13.3	5.4
(270)	359	1.33	9.1	3.7	17.3	6.9
290	384	1.32	11.2	4.8	21.3	9.1
300	396	1.32	12.7	5.6	24.2	10.6
320	425	1.33	15.4	6.7	29.3	12.8
350	465	1.33	19.7	9.0	37.5	17.1
385	505	1.31	24.6	11.4	46.7	21.7
400	525	1.31	27.7	13.0	52.7	24.8
(425)	556	1.31	30.9	14.4	58.7	27.3
450	590	1.31	36.2	17.0	68.8	32.3
(500)	655	1.31	44.1	20.0	83.8	37.9
(550)	720	1.31	52.3	21.8	99.3	41.5

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.

(*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS

TOP	82%	ISO 2470-2
-----	-----	------------

TOLERANCES - SAMPLING ISO 186

SUBSTANCE	+/- 2%	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
STIFFNESS	- 15%	for single determinations (95% of values)
BRIGHTNESS	+/- 2	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2