

TECHNICAL SPECIFICATION

DECEMBER 2025

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mNm	mNm	mNm	mNm
250	325	1.30	7.0	3.1	12.3	5.6
275	358	1.30	9.0	4.1	16.8	7.6
300	390	1.30	12.2	5.5	20.6	9.5
325	423	1.30	15.2	6.9	27.0	12.0
350	455	1.30	19.1	8.6	35.7	15.9
375	488	1.30	23.0	10.2	44.0	19.2
400	520	1.30	27.0	12.3	55.0	23.5
425	553	1.30	31.4	14.8	63.0	28.5
450	585	1.30	36.8	17.3	71.0	30.9
475	618	1.30	42.1	19.6	82.0	37.3
500	650	1.30	47.0	22.1	89.0	41.0
550	715	1.30	49.0	24.5	115.0	53.0

(*) L&W VALUES ARE GUARANTEED. TABER FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	82%	ISO 2470-2

TOLERANCES - SAMPLING ISO 186	
SUBSTANCE	+/- 5%
CALIPER	+/- 5%
STIFFNESS	- 15%
BRIGHTNESS	+/- 1
TEST CONDITIONS	T: 23° C +/- 1 RH: 50% +/- 2