



TRIPLEX GRIS
 COATED WHITE LINED CHIPBOARD
 (WLC) WITH GREY BACK
GD 2

PROVISIONAL TECHNICAL SPECIFICATION

FEBRUARY 2025

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)		STIFFNESS L&W *(5°)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mNm	mNm	mNm	mNm
250	350	1.40	8.0	4.8	15.5	9.0
275	385	1.40	10.8	5.1	20.8	9.7
300	422	1.41	13.5	5.6	27.0	11.0
325	455	1.40	17.0	6.4	33.0	12.4
350	489	1.40	20.0	7.9	40.0	15.7
375	529	1.41	24.6	9.8	49.0	19.4
400	558	1.40	29.6	12.0	59.2	23.8
425	595	1.40	35.1	13.1	68.6	25.4
450	630	1.40	41.6	15.7	80.3	30.3
475	665	1.40	47.0	17.4	91.6	33.9

(*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	82%	ISO 2470-2

TOLERANCES - SAMPLING ISO 186 (*)		
SUBSTANCE	+/- 4%	
CALIPER	+/- 5%	
STIFFNESS	- 15%	
BRIGHTNESS	+/- 2	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

(*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.

