



OVARO 906
 PASTED GREY BOARD WITH TWO AVANA SIDES
 GK

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
720	1.00	1.39
1100	1.60	1.45
1240	1.90	1.53
1350	2.00	1.48

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
1400	2.10	1.50
1590	2.40	1.51
1880	3.00	1.60
2500	4.00	1.60

BRIGHTNESS		
TOP	/	ISO 2470
BACK	/	ISO 2470

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 5%	average of order
MOISTURE ISO 287	7.0% + 2 / - 1.0	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
BRIGHTNESS	/	for single determinations (95% of values)
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

