



OVARO 925
 LAMINATED TWO SIDES
 EXTRA WHITE LINED BOARD
 GK

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
575	0.70	1.22
600	0.87	1.45
660	0.95	1.44
690	1.00	1.45

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
880	1.30	1.48
940	1.40	1.49
980	1.50	1.53
1060	1.60	1.51

BRIGHTNESS		
TOP	85%	ISO 2470
BACK	85%	ISO 2470

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 5%	average of order
MOISTURE ISO 287	7.0% + 2.0 / - 1.0	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
BRIGHTNESS	Lim. inf. - 2	for single determinations (95% of values)
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

