



OVARO 935
 LAMINATED BOARD WITH TWO COATED
 WHITE SIDES
 GD

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
825	1.00	1.22
885	1.10	1.23
1020	1.30	1.30
1115	1.50	1.34
1185	1.60	1.37
1305	1.80	1.39

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
1365	1.90	1.40
1425	2.00	1.42
1485	2.10	1.43
1595	2.40	1.50
(2065)	3.00	1.48
(2360)	3.50	1.50

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.

BRIGHTNESS		
TOP	80%	ISO 2470
BACK	80%	ISO 2470

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 5%	average of order
MOISTURE ISO 287	7.0% + 2.0 / - 1.0	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
BRIGHTNESS	Lim. inf. - 2	for single determinations (95% of values)
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

