

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
800	1.20	1.50
882	1.40	1.59
945	1.50	1.59
1008	1.60	1.59
1071	1.70	1.59
1100	1.75	1.59
1134	1.80	1.59
1197	1.90	1.59
1260	2.00	1.59
1323	2.10	1.59
1386	2.20	1.59
1449	2.30	1.59
1512	2.40	1.59

SUBSTANCE	CALIPER	BULK
ISO 536	ISO 534	ISO 534
g/m²	mm	cm³/g
1575	2.50	1.59
1701	2.70	1.59
1764	2.80	1.59
1827	2.90	1.59
1890	3.00	1.59
1953	3.10	1.59
2016	3.20	1.59
2079	3.30	1.59
2142	3.40	1.59
2205	3.50	1.59
2331	3.70	1.59
2394	3.80	1.59
2520	4.00	1.59

BRIGHTNESS		
TOP	/	ISO 2470
BACK	/	ISO 2470

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 5%	average of order
MOISTURE ISO 287	7.5% + 1.5 / - 1.0	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
BRIGHTNESS	/	for single determinations (95% of values)
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2