

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)		STIFFNESS L&W *(5°)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mNm	mNm	mNm	mNm
290	389	1.34	10.9	5.4	20.6	10.2
300	405	1.34	12.3	6.0	23.3	11.3
320	430	1.34	14.6	7.2	27.6	13.6
350	472	1.35	18.7	9.1	35.4	17.1
400	540	1.35	26.6	12.8	50.2	24.1
(450)	605	1.35	34.7	16.8	65.5	31.7

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.
 (*) TABER FIGURES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS (AT PRODUCTION)		
TOP	83%	ISO 2470-2

COBB - ISO 535		
COBB BACK 60'	30-450 g/m ²	ISO 535

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 2%	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
STIFFNESS	- 15%	for single determinations (95% of values)
BRIGHTNESS	+/- 1	ISO 2470-2
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2