



SYROS ESTUCADO GT2
 FULLY COATED WHITE LINED CHIPBOARD
 (WLC) WITH MANILLA BACK
GT 2

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m ²	µm	cm ³ /g	mNm	mNm	mNm	mNm
250	315	1.26	7.0	3.1	10.3	5.4
275	345	1.25	9.0	4.1	12.6	6.7
280	350	1.25	9.4	4.2	14.2	7.2
300	395	1.32	12.2	5.5	18.9	8.9
325	425	1.31	15.2	6.9	23.6	11.6
350	465	1.33	19.1	8.6	29.3	13.8
375	500	1.33	23.0	10.2	40.6	17.2
400	535	1.34	27.0	12.3	44.1	21.4
425	560	1.32	31.4	14.8	61.9	26.5
450	600	1.33	36.8	17.3	67.2	29.9
475	630	1.33	42.1	19.6	77.3	37.8
500	670	1.34	47.0	22.1	87.5	42.7

(*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	78%	DIN 5033

TOLERANCES - SAMPLING ISO 186 (*)	
SUBSTANCE	+/- 5%
CALIPER	+/- 5%
STIFFNESS	- 15%
BRIGHTNESS	+/- 1
TEST CONDITIONS	T: 23° C +/- 1

(*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.

