



SYROS MICROPRINT
COATED WHITE LINED CHIPBOARD
(WLC) WITH GREY BACK
GD-LINER

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)		STIFFNESS L&W *(5°)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mNm	mNm	mNm	mNm
190	215	1.13	2.1	1.1	5.3	2.7
200	230	1.15	3.1	1.4	6.0	3.1
210	245	1.17	3.4	1.7	6.7	3.5
220	260	1.18	4.0	1.9	7.5	3.8
230	280	1.22	4.5	2.1	8.6	4.4
250	310	1.26	6.7	2.9	11.3	5.3
275	345	1.25	8.5	3.6	15.5	6.8

(*) TABER FIGURES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	78%	DIN 5033

TOLERANCES - SAMPLING ISO 186	
SUBSTANCE	+/- 5%
CALIPER	+/- 5%
STIFFNESS	- 15%
BRIGHTNESS	+/- 1
TEST CONDITIONS	T: 23° C +/- 1 RH: 50% +/- 2

