



TRIPLEX GRIS
COATED WHITE LINED CHIPBOARD
(WLC) WITH GREY BACK
GD 2

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)		STIFFNESS L&W *(5°)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mNm	mNm	mNm	mNm
250	330	1.32	8.0	3.6	15.5	6.8
275	363	1.32	10.8	4.8	20.8	9.1
300	396	1.32	13.5	6.0	27.0	11.8
325	429	1.32	17.0	7.5	33.0	14.5
350	462	1.32	20.0	8.8	40.0	17.5
375	495	1.32	24.6	10.8	49.0	21.4
400	528	1.32	29.6	13.0	59.2	25.8
425	561	1.32	35.1	15.4	68.6	29.9
450	594	1.32	41.6	18.2	80.3	35.1
475	627	1.32	47.0	20.5	91.6	39.9

(*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	79.5%	ISO 2470-2

TOLERANCES - SAMPLING ISO 186 (*)		
SUBSTANCE	+/- 4%	
CALIPER	+/- 5%	
STIFFNESS	- 15%	
BRIGHTNESS	+/- 1.5	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

(*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.

