



TRIPLEX BLANCO
FULLY COATED WHITE LINED CHIPBOARD
(WLC) WITH WHITE BACK
GT 1

TECHNICAL SPECIFICATION

OCTOBER 2022

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m ²	µm	cm ³ /g	mNm	mNm	mNm	mNm
250	338	1.35	9.1	4.2	18.5	8.5
275	375	1.36	11.6	5.2	24.0	11.0
300	407	1.36	14.3	6.4	28.0	12.8
325	445	1.37	18.1	8.1	36.0	16.5
350	485	1.38	22.1	9.9	44.0	20.2
375	530	1.41	26.6	11.9	54.0	24.4
400	555	1.39	32.0	14.3	65.0	29.4
425	585	1.38	38.0	16.8	72.2	34.8
450	620	1.37	43.4	19.0	85.9	39.0

(*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	79.5%	ISO 2470-2
BACK	74.5%	ISO 2470-2

TOLERANCES - SAMPLING ISO 186 (*)		
SUBSTANCE	+/- 4%	
CALIPER	+/- 5%	
STIFFNESS	- 15%	
BRIGHTNESS TOP/BACK	+/- 1.5	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

(*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.

