



VINCIBRIGHT
FULLY COATED WHITE LINED CHIPBOARD
(WLC) WITH MANILLA BACK
GT 2

TECHNICAL SPECIFICATION

OCTOBER 2022

| SUBSTANCE | CALIPER | BULK | STIFFNESS TABER 15° (*) | | STIFFNESS L&W 5° (*) | |
|------------------|---------|--------------------|-------------------------|------|----------------------|------|
| | | | MD | CD | MD | CD |
| ISO 536 | ISO 534 | ISO 534 | ISO 2493 | | DIN 53121 | |
| g/m ² | µm | cm ³ /g | mNm | mNm | mNm | mNm |
| (270) | 359 | 1.33 | 9.1 | 3.7 | 17.3 | 6.9 |
| 290 | 384 | 1.32 | 11.2 | 4.8 | 21.3 | 9.1 |
| 320 | 425 | 1.33 | 15.4 | 6.7 | 29.3 | 12.8 |
| 350 | 465 | 1.33 | 19.7 | 9.0 | 37.5 | 17.1 |
| 385 | 505 | 1.31 | 24.6 | 11.4 | 46.7 | 21.7 |
| 400 | 525 | 1.31 | 27.7 | 13.0 | 52.7 | 24.8 |
| (425) | 556 | 1.31 | 30.9 | 14.4 | 58.7 | 27.3 |
| 450 | 590 | 1.31 | 36.2 | 17.0 | 68.8 | 32.3 |
| (480) | 630 | 1.31 | 41.0 | 18.7 | 77.8 | 35.5 |
| (500) | 655 | 1.31 | 44.1 | 20.0 | 83.8 | 37.9 |

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.
 (*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

| BRIGHTNESS (AT PRODUCTION) | | |
|-----------------------------------|-----|------------|
| TOP | 82% | ISO 2470-2 |
| BACK | 55% | ISO 2470-2 |

| TOLERANCES - SAMPLING ISO 186 | | |
|--------------------------------------|-----------------------|--|
| SUBSTANCE | +/- 2% | average of order |
| CALIPER | +/- 5% | for single determinations (95% of values) |
| STIFFNESS | - 15% | for single determinations (95% of values) |
| BRIGHTNESS TOP/BACK | +/- 2 | |
| TEST CONDITIONS | T: 23° C +/- 1 | RH: 50% +/- 2 |

