



SYROS DUO BROWN

BROWN TOP AND BROWN BACK
UD

TECHNICAL SPECIFICATION

DECEMBER 2025

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mNm	mNm	mNm	mNm
190	270	1.42	3.5	1.5	8.4	3.3
220	305	1.38	5.5	2.3	10.5	4.1
250	335	1.34	6.7	3.1	12.6	5.7
275	365	1.33	8.6	4.0	17.1	7.7
300	410	1.37	11.8	5.3	20.8	9.6
325	435	1.34	14.6	6.7	27.2	12.1
350	470	1.34	18.3	8.3	35.8	16.0
375	510	1.36	22.4	9.8	43.9	19.2
400	545	1.36	25.8	11.9	54.6	23.4
425	575	1.35	30.0	14.3	62.2	28.1
450	610	1.36	35.2	16.6	69.8	30.4
475	645	1.36	40.2	18.8	80.3	36.5
500	680	1.36	44.8	21.2	86.3	39.7

(*) L&W VALUES ARE GUARANTEED. TABER FIGURES ARE CALCULATED.

COBB - ISO 535

COBB TOP / BACK 60'	<60 g/m²	ISO 535
---------------------	----------	---------

TOLERANCES - SAMPLING ISO 186 (*)

SUBSTANCE	+/- 5%
CALIPER	+/- 5%
STIFFNESS	- 15%
TEST CONDITIONS	T: 23° C +/- 1

(*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.