



**SYROS DUO BROWN**  
**BROWN TOP AND BROWN BACK**  
**UD**

**TECHNICAL SPECIFICATION**

**JANUARY 2025**

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
<b>g/m<sup>2</sup></b>	<b>µm</b>	<b>cm<sup>3</sup>/g</b>	<b>mNm</b>	<b>mNm</b>	<b>mNm</b>	<b>mNm</b>
250	335	1.34	6.7	3.1	12.6	5.7
275	365	1.33	8.6	4.0	17.1	7.7
300	410	1.37	11.8	5.3	20.8	9.6
325	435	1.34	14.6	6.7	27.2	12.1
350	470	1.34	18.3	8.3	35.8	16.0
375	510	1.36	22.4	9.8	43.9	19.2
400	545	1.36	25.8	11.9	54.6	23.4
425	575	1.35	30.0	14.3	62.2	28.1
450	610	1.36	35.2	16.6	69.8	30.4
475	645	1.36	40.2	18.8	80.3	36.5
500	680	1.36	44.8	21.2	86.3	39.7

(\*) L&W VALUES ARE GUARANTEED. TABER FIGURES ARE CALCULATED.

**COBB - ISO 535**

COBB TOP / BACK 60'	<60 g/m <sup>2</sup>	ISO 535
COBB TOP / BACK 180' (*)	<60 g/m <sup>2</sup>	ISO 535

(\*) OPTIONAL TREATMENT, AVAILABLE ON REQUEST ONLY

**TOLERANCES - SAMPLING ISO 186 (\*)**

SUBSTANCE	+/- 5%
CALIPER	+/- 5%
STIFFNESS	- 15%
TEST CONDITIONS	T: 23° C +/- 1

(\*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.

