



**TRIPLEX GRIS**  
**COATED WHITE LINED CHIPBOARD**  
**(WLC) WITH GREY BACK**  
**GD 2**

**TECHNICAL SPECIFICATION**

**JANUARY 2025**

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m <sup>2</sup>	µm	cm <sup>3</sup> /g	mNm	mNm	mNm	mNm
300	407	1.36	13.5	6.0	27.0	11.8
325	445	1.37	17.0	7.5	33.0	14.5
350	485	1.38	20.0	8.8	40.0	17.5
375	530	1.41	24.6	10.8	49.0	21.4
400	555	1.39	29.6	13.0	59.2	25.8
425	585	1.38	35.1	15.4	68.6	29.9
450	620	1.37	41.6	18.2	80.3	35.1
475	670	1.41	47.0	20.5	91.6	39.9

(\*) L&W VALUES ARE GUARANTEED. TABER FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	82.0%	ISO 2470-2

COBB - ISO 535		
COBB BACK 60' WR (*)	<60 g/m <sup>2</sup>	ISO 535

(\*) OPTIONAL TREATMENT, AVAILABLE ON REQUEST ONLY.

TOLERANCES - SAMPLING ISO 186 (*)	
SUBSTANCE	+/- 4%
CALIPER	+/- 5%
STIFFNESS	- 15%
BRIGHTNESS	+/- 1.5
TEST CONDITIONS	T: 23° C +/- 1                      RH: 50% +/- 2

(\*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.

