



**TRIPLEX GRIS**  
**COATED WHITE LINED CHIPBOARD**  
**(WLC) WITH GREY BACK**  
**GD 2**

**TECHNICAL SPECIFICATION**

**JANUARY 2025**

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)		STIFFNESS L&W *(5°)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
<b>g/m<sup>2</sup></b>	<b>µm</b>	<b>cm<sup>3</sup>/g</b>	<b>mNm</b>	<b>mNm</b>	<b>mNm</b>	<b>mNm</b>
250	330	1.32	8.0	3.6	15.5	6.8
275	363	1.32	10.8	4.8	20.8	9.1
300	396	1.32	13.5	6.0	27.0	11.8
325	429	1.32	17.0	7.5	33.0	14.5
350	462	1.32	20.0	8.8	40.0	17.5
375	495	1.32	24.6	10.8	49.0	21.4
400	528	1.32	29.6	13.0	59.2	25.8
425	561	1.32	35.1	15.4	68.6	29.9
450	594	1.32	41.6	18.2	80.3	35.1
475	627	1.32	47.0	20.5	91.6	39.9

(\*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

<b>BRIGHTNESS</b>		
TOP	82%	ISO 2470-2

<b>TOLERANCES - SAMPLING ISO 186 (*)</b>		
SUBSTANCE	+/- 4%	
CALIPER	+/- 5%	
STIFFNESS	- 15%	
BRIGHTNESS	+/- 1.5	
TEST CONDITIONS	<b>T:</b> 23° C +/- 1	<b>RH:</b> 50% +/- 2

(\*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.

