



VINCIWHITE
FULLY COATED WHITE LINED CHIPBOARD
(WLC) WITH WHITE BACK
GT 1

TECHNICAL SPECIFICATION

JANUARY 2025

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m ²	μm	cm ³ /g	mNm	mNm	mNm	mNm
(260)	345	1.33	8.4	3.6	16.0	6.8
290	378	1.30	10.7	4.6	20.4	8.8
320	415	1.30	14.8	6.5	28.1	12.4
350	448	1.28	19.0	8.7	36.1	16.6
(385)	488	1.27	23.7	11.1	45.0	21.1
400	508	1.27	26.8	12.6	50.8	23.9
450	573	1.27	35.2	16.5	66.8	31.3

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.
 (*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS (AT PRODUCTION)

TOP	82%	ISO 2470-2
BACK	77%	ISO 2470-2

TOLERANCES - SAMPLING ISO 186

SUBSTANCE	+/- 2%	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
STIFFNESS	- 15%	for single determinations (95% of values)
BRIGHTNESS TOP/BACK	+/- 2	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

