

TECHNICAL SPECIFICATION

DECEMBER 2025

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER *(15°)		STIFFNESS L&W *(5°)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mNm	mNm	mNm	mNm
(230)	300	1.30	5.2	2.2	9.8	4.1
(250)	328	1.31	7.0	2.8	13.3	5.4
(270)	359	1.33	9.1	3.7	17.3	6.9
(290)	384	1.32	11.2	4.8	21.3	9.1
(300)	396	1.32	12.7	5.6	24.2	10.6
(320)	425	1.33	15.4	6.7	29.3	12.8

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.
 (*) TABER FIGURES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS (AT PRODUCTION)

TOP	82%	ISO 2470-2
-----	-----	------------

TOLERANCES - SAMPLING ISO 186

SUBSTANCE	+/- 2%	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
STIFFNESS	- 15%	for single determinations (95% of values)
BRIGHTNESS	+/- 2	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2