



SYROS ESTUCADO
COATED WHITE LINED CHIPBOARD
(WLC) WITH GREY BACK
GD

TECHNICAL SPECIFICATION

APRIL 2026

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m ²	µm	cm ³ /g	mNm	mNm	mNm	mNm
250	320	1.28	7.0	3.0	12.6	5.4
275	350	1.27	8.6	4.1	16.0	7.6
300	380	1.27	10.0	4.9	18.0	8.4
325	410	1.26	13.0	5.6	23.1	9.7
350	440	1.26	16.0	7.0	29.9	12.9
375	470	1.25	20.8	8.5	39.7	16.0
400	500	1.25	24.0	9.0	48.7	17.2
425	535	1.26	29.0	11.0	58.3	21.2
450	565	1.26	33.0	13.5	63.4	24.0
475	600	1.26	35.0	14.5	68.3	27.6
500	630	1.26	38.0	19.0	71.8	35.3
550	690	1.25	49.0	28.0	102.9	54.6

(*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	82%	ISO 2470-2

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 5%	
CALIPER	+/- 5%	
STIFFNESS	- 15%	
BRIGHTNESS	+/- 1	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

